


礦物顏料名稱編號對照表

尖晶石黃 (861)	暗橘 (823)	天然褐 (915)	薄荷綠 (868)
陽光黃 (867)	喜耶拿紅 (824)	棕黑褐 (916)	尖晶石土耳其藍 (862)
尖晶石橘 (865)	赭紅 (803)	暗褐 (826)	尖晶石藍 (863)
義大利金赭 (821)	紅褐 (808)	綠褐·塞浦路斯 (827)	群藍 (855)
赭黃 (802)	紅棕褐 (825)	暗綠褐 (807)	群紫 (856)
赭橘·普羅旺斯 (822)	鹿褐 (805)	尖晶石綠 (864)	氧化鐵黑 (850)


調色濃淡所需顏料色母比例

A	B	C
蛋白膠細緻面漆		
每 1 kg 粉料 (白色) + 100 g 顏料色母	每 1 kg 粉料 (白色) + 35 g 顏料色母	每 1 kg 粉料 (白色) + 7.5 g 顏料色母
石灰粉光料 (粗、細、超細)		
每 1 kg 粉料 (白色) + 50 g 顏料色母	每 1 kg 粉料 (白色) + 17.5 g 顏料色母	每 1 kg 粉料 (白色) + 3.75 g 顏料色母
灰泥塗料 (細緻、含顆粒) / 水玻璃礦物塗料 (粗顆粒、細顆粒)		
每 1 L 塗料 (白色) + 100 g 顏料色母	每 1 L 塗料 (白色) + 35 g 顏料色母	每 1 L 塗料 (白色) + 7.5 g 顏料色母


* 電腦螢幕或印刷品所呈現的色調會有所偏差，本色卡僅供參考。



尖晶石黃 (861)




陽光黃 (867)




尖晶石橘 (865)




義大利金赭 (821)



赭黃 (802)



赭橘·普羅旺斯 (822)




暗橘 (823)




喜耶拿紅 (824)




赭紅 (803)




紅褐 (808)



紅棕褐 (825)




鹿褐 (805)




天然褐 (915)



棕黑褐 (916)



暗褐 (826)




綠褐·塞浦路斯 (827)



暗綠褐 (807)



尖晶石綠 (864)




薄荷綠 (868)




尖晶石土耳其藍 (862)



尖晶石藍 (863)



群藍 (855)



群紫 (856)



氧化鐵黑 (850)